Argonne National Laboratory is a U.S. Department of Energy laboratory managed by UChicago Argonne, LLC.

Free energies of the first hydrogenation steps of competing reactions was compared.

- In all cases the formation of OCHO* is preferred to the formation of H*
- \bullet CO₂ reduction is more favorable than production of hydrogen gas

 $OH^* + H^+ + e^- \rightarrow H_2O$ $CO_2 + H^+ + e^- \rightarrow OCHO^*$ $OCHO^* + H^+ + e^- \rightarrow HCOOH^*$ $HCOOH^* \rightarrow CHO^* + H_2O$ CHO^{*} **Most probable rate limiting steps to CH**₄ OH^* \longleftarrow

The optimal binding configuration for all of the intermediates for possible rate

One way of preventing this increase, is to convert $CO₂$ into useful hydrocarbons such as methane. Current catalysts for this conversion are not efficient, and as such our group is screening for potential new catalysts for this conversion.

Five Cu-Pd alloy clusters were screened for the electrochemical $CO₂$ reduction based on density functional theory (DFT)

- Vienna Ab-initio Simulation Package (VASP)
- PBE exchange–correlation functional
- van der Waals (vdW) interaction (D2 method)

▪ **"Rapid growth in carbon dioxide emissions breaks in 2015." CSIRO. https://www.csiro.au/en/News/News-releases/2015/Rapid-growth-in-carbon-dioxide-emissions-breaks-in-2015.**

Free energies were calculated based on the computational hydrogen electrode model

- Carbon prefers to bond to Pd, and oxygen prefers to bond to Cu
- Elementary limiting potentials and overpotentials (in V) \blacksquare The bonding of C and O also depends on an atom's coordination number

ELECTROCHEMICAL REDUCTION OF CO² USING Cu-Pd CLUSTERS ON GRAPHENE

Marcus Ochsendorf,^{†‡} Haiying He,^{†‡} Peter Zapol[†]

†Materials Science Division, Argonne National Laboratory; ‡Department of Physics and Astronomy, Valparaiso University

Over the past decade, the amount of $CO₂$ in the atmosphere has increased drastically, creating adverse climate effects. We must ensure that the level of $CO₂$ in the atmosphere doesn't increase

References

Future Direction

- \blacksquare The electronic structure of the Cu₂Pd cluster on graphene will be analyzed to better understand the bonding that occurs during the reaction
- More clusters doped on graphene will be screened to determine if they could be good catalysts for the electrochemical reduction of CO₂

Motivation Computational Method

First, the cluster geometry in gas phase was optimized to find the stable state.

The clusters were then placed on a single vacancy graphene support. Different binding sites and orientations were tested.

All the clusters are found to bind strongly to the vacancy site and are very unlikely to move and aggregate.

Optimizing Clusters

Results and Discussion

G relative -0.59 eV \vert -1.12 eV -1.59 eV -0.99 eV -0.91 eV

Screening

Figure 3: The optimized configurations of the first hydrogenation for the reduction of $CO₂$ and the production of $H₂$ (red: O, small blue: H). The relative energy associated with each of the configuration is the free energy of the configuration with respect to the sum of energies of reactants.

- Rate limiting step: CHO* formation for triatomic clusters OH* desorption for other clusters
- **The cluster that appears to make the best catalyst is** $Cu₂Pd$